

KingRep[®] MM50

Low viscosity MMA crack sealer.

DESCRIPTION

KingRep MM50 is a 100% reactive ultra-low viscous, two-component methyl methacrylate resin specially designed for use as a penetrating crack sealer or to fortify extremely porous concrete substrates. The very low viscosity and low surface tension of KingRep MM50 allows it to easily penetrate and fill deep cracks in existing concrete. The mixed product is poured directly into the cracks or fed by gravity injection directly into the crack whereby the capillary action draws the product deep into the substrate and both fills and heals the crack restoring strength and performance.

APPLICATIONS

KingRep MM50 is designed for crack sealing and filling in multiple types of concrete structures such as:

- ☒ Parking garages.
- ☒ Factory and industrial floors.
- ☒ Concrete bridge decks.
- ☒ Aircraft runways, hangars and aprons.
- ☒ Precast concrete elements.
- ☒ Premature cracking in new concrete.
- ☒ PQC pavement.

ADVANTAGES

- ☒ Very low viscosity, for excellent absorption into concrete.
- ☒ Fast cure time, for rapid recoat and return to service.
- ☒ Fills and bonds cracks.
- ☒ Easy application.
- ☒ Low VOC content.
- ☒ Protects against water penetration.
- ☒ May be used over a wide temperature range.

METHOD OF USE

SURFACE PREPARATION

The substrate should be sound, clean and free from dirt, wax, curing agents and any contamination. Surface laitance should be removed by grit blasting or water jetting. KingRep MM50 should not be installed on fresh concrete until maximum shrinkage has occurred (at least 30 days after placement).

MIXING

KingRep MM50 consists of two components, a resin and powder hardener. The quantity of hardener has to be adjusted to the substrate temperature (see table).

TECHNICAL PROPERTIES

Colour:	Clear
Density:	0.99 ± 0.02 g/cm ³
Viscosity Brookfield:	10 Cps @ 23oC
Shore D Hardness ASTM D2240	> 80
Tensile strength: ASTM D638	55 ± 5 MPa
Elongation at break: ASTM D638	5 ± 1%
Compressive strength @ 24 hrs: ASTM C3986	86 ± 5 MPa
Flexural strength:	82 ± 5 MPa
Water absorption: ASTM D570	0.75 - 0.8%/ 24 hr
VOC:	< 50 g/ltr (comply with LEED)

At temperatures below 5oC, KingRep MM50 Accelerator need to be used, consult KINGKRETE Technical department for the proper amount of accelerator to be used.

POT LIFE/ HARDENING

The potlife time and curing of KingRep MM50 are dependent on temperature and the quantity of hardener.

Temperature (oC)*	Hardener (%pbw)**	Pot Life (min)***	Hardening time (min)
5 - 10	5.0	≈ 15	≈ 60
10 - 15	4.0	≈ 12 - 16	≈ 45 - 50
15 - 20	3.0	≈ 15 - 20	≈ 45 - 50
20 - 25	2.0	≈ 15 - 20	≈ 45 - 50
25 - 30	1.0	≈ 20 - 25	≈ 45 - 50
30 - 40	1.0	≈ 5 - 10	≈ 30 - 35
+40	1.0	≈ 5 - 10	≈ 25 - 30

Notes: * Temperature statements refer to resin-, floor- and air- temperature. **Do not use less than 1% hardener percentage, unless it is confirmed at site. *** The indication of the approximate pot life always refers to the lower temperature.

APPLICATION

General Installation Instructions for Crack Sealing

Cracks must be clean and dry. Clean out cracks with oil-free compressed air. A hot lance may be used and



KingRep[®] MM50

Low viscosity MMA crack sealer.

provides excellent preparation however maximum substrate temperature at application must be observed.

KingRep MM50 should be fed directly into the cracks one by one along their entire length until completely full and rejection of more product.

Varying techniques can be applied for an acceptable result.

Agricultural syringes can be loaded and used to dispense directly into small cracks, the mixed product can be poured directly into larger cracks from an acceptable container. Creating a temporary dam from low quality sealant along the sides of the crack can assist with direct pouring. The caulking is later removed.

Overflows onto the surface are sometimes inevitable and will only result in fortifying the area adjacent the crack.

General Installation Instructions for surface Treatment

If the pavement surface is to be sealed, it should be lightly (brush blast) shot blasted to remove laitance and expose surface cracks.

Inspect the underside of elevated decks for evidence of full depth cracking that may require additional treatment to prevent draining of the resin.

Cracks greater than 3 mm width should be repaired individually prior to application of flood coat. Fill cracks larger than 3 mm with loose sand and pour small quantity of mixed KingRep MM50 into the crack and spread with a paint brush, allow curing before applying flood coat.

KingRep MM50 is spread evenly on the surface as a flood coat with a squeegee or rollers and allowed to absorb completely into the concrete substrate. Do not allow to form puddles.

NOTES

Always prepare the proper amount of materials to be applied to the working area.

Freshly applied KingRep MM50 must be protected from damp, condensation and water for at least 1 hour.

CLEANING

All tools should be cleaned immediately using KINGKRETE Solvent, lacquer thinner or MEK. Hardened material must be cleaned mechanically.

PACKAGING

KingRep MM50 is available in 19 litre pails.

COVERAGE

Approximately 2.0 – 2.5 m²/ltr per coat. However, coverage may vary depending on the surface porosity, size, and quantity of cracks present in the area being treated. Two coats may be necessary for very porous surfaces.

STORAGE

Shelf life is 1 year when stored under cover, out of direct sunlight and protected from extremes of temperature. Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult KingKrete's Technical Services Department.

HEALTH AND SAFETY

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs. Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Reseal containers after use. Use in well ventilated areas and avoid inhalation.

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local KingKrete representative. KingKrete Inc. reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY AND CARE

All products originating from KingKrete's Middle East facility are manufactured under a management system independently certified to conform to the requirements of the quality standards ISO 9001, ISO 14001 and ISO 45001.

* Properties listed are based on laboratory-controlled tests.

® = Registered trademark of the KingKrete-Group in many countries.



KingRep[®] MM50

Low viscosity MMA crack sealer.

Ref: KK-03036-MEA-R01 | Issue: 01.2026

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this KingKrete Inc. publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by KingKrete Inc. either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not KingKrete Inc. are responsible for carrying out procedures appropriate to a specific application.

KingKrete Middle East
Qatar – Syria
www.kingkrete.com

Disclaimer: the IAS mark relates to certified management system and not to the product mentioned on this datasheet

