



KingRep® Primer EPBM

Epoxy resin based primer for KingRep.

DESCRIPTION

KingRep Primer EPBM is a clear high performance solvent free epoxy primer designed to improve adhesion of KingRep EPBM on concrete and steel substrates.

APPLICATIONS

KingRep Primer EPBM is used as a prime coat to improve adhesion of subsequent KingRep EPBM layers on concrete and steel substrates.

METHOD OF USE

Substrate Preparation

The substrate must be clean, dry, even, dense and free from oil, grease, dust and other contaminants. A clean surface will ensure maximum adhesion between the substrate and the coating.

The concrete substrate should be below 75% RH and have less than 4% moisture content. Alternatively, consult with KINGKRETE's Technical Department.

SURFACE PREPARATION

The surface must be structurally sound, free from oil, grease and other forms of contamination.

Concrete should be surface dry and suitably prepared either by scabbling or grit blasting to remove any surface laitance. Steel surfaces should be grit blasted to remove all rust and scale. (See the KINGKRETE Guide to Surface Preparation for further details).

MIXING

Prior to mixing, stir individual components of KingRep Primer EPBM. Take care to ensure that bottom and sides are thoroughly scraped, transfer the entire content of hardener into the base and mix for 2 - 3 minutes using slow speed mixer fitted with suitable paddle.

APPLICATION

KingRep Primer EPBM should be applied by brush or short hair lambs wool roller. Spread evenly at the recommended coverage rate, avoiding any primer ponding on the floor. The primer should be applied so that the surface is thoroughly wet, ensuring there is a continuous film of resin over the surface.

Highly porous surfaces may require two coats of KingRep Primer EPBM. It is highly important that KingRep EPBM is applied whilst the primer is very tacky.

TECHNICAL PROPERTIES

Appearance:	Yellowish clear liquid
Bond strength: ASTM D4541	≥ 2 MPa (concrete failure)
Mixed density:	1.1 ± 0.05 g/cm ³
Mixed viscosity:	5 - 15 poise
Pot life:	90 - 120 min
Over coating time:	12 - 24 hr
VOC:	< 20 g/ltr

CLEANING

KingRep Primer EPBM can be removed by KINGKRETE solvent prior to setting.

PACKAGING

KingRep Primer EPBM is available in 5 kg packs.

COVERAGE

5 m²/kg; 200 micron DFT.

STORAGE

Shelf life is 1 year when stored under cover, out of direct sunlight and protected from extremes of temperature. Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult KingKrete's Technical Services Department.

HEALTH AND SAFETY

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs. Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Reseal containers after use. Use in well ventilated areas and avoid inhalation.

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local KingKrete representative. KingKrete Inc. reserves the right to have the true cause of any difficulty determined by accepted test methods.



KingRep® Primer EPBM

Epoxy resin based primer for KingRep.

QUALITY AND CARE

All products originating from KingKrete's Middle East facility are manufactured under a management system independently certified to conform to the requirements of the quality standards ISO 9001, ISO 14001 and ISO 45001.

* Properties listed are based on laboratory-controlled tests.
® = Registered trademark of the KingKrete-Group in many countries.

Ref: KK-03040-MEA-R01 | Issue: 01.2026

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this KingKrete Inc. publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by KingKrete Inc. either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not KingKrete Inc. are responsible for carrying out procedures appropriate to a specific application.

