

KingGrout® PE10

High strength polyester grout for anchoring and fixing.

DESCRIPTION

KingGrout PE10 is a two components, high strength, fast cure, polyester resin anchoring grout.

APPLICATIONS

KingGrout PE10 is ideally designed for use in the following applications:

- ☒ Permanent installation of reinforcement starter bars and dowel bars.
- ☒ Permanent installation of hand rails, safety fence, wall ties, railway tracks and ground anchors.

ADVANTAGES

- ☒ Exceptional rapid strength development.
- ☒ Resistant to dynamic loading.
- ☒ Damp tolerant. The product will cure under damp conditions and is resistant to immersion underwater.
- ☒ Exceptional high compressive, flexural and tensile strengths.
- ☒ Extremely dense.
- ☒ Exceptional bond to concrete and steel surfaces.
- ☒ Good chemical resistance.
- ☒ High ultimate and early strengths. Available into two grade, KingGrout PE10 H (Horizontal) and KingGrout PE10 V (Vertical).

METHOD OF USE

Substrate preparation

Substrate should be sound, clean and free from grease or any contamination. Bars should be free from any loose rust deposits. Holes are best made using rotary percussive drill to provide rough sides followed by air or water flushing. If hole is cast, it should be of inverse dovetail configuration or mechanically roughened to provide a key. Deformed or ribbed bars will give a higher performance than smooth or other bar types.

MIXING

To ensure proper mixing, a mechanically powered mixer or drill fitted with suitable paddle should be used. The entire content of the resin should be transferred to a plastic container.

TECHNICAL PROPERTIES

Compressive strength: BS6319, Part 2 : 1983	≥ 70 MPa @ 1 hr ≥ 100 MPa @ 24 hr ≥ 115 MPa @ 7 days
Flexural strength: BS6319, Part 3 : 1990	≥ 25 MPa @ 7 days
Tensile strength: BS6319, Part 7 : 1985	≥ 14 MPa @ 7 days
Working life:	90 min @ 10°C 35 min @ 20°C 14 min @ 30°C
Bond strength:	When applied properly, failure in pull will be in the concrete or steel, and not at the bond interface.

Mixing shall continue for 3 minutes or until a uniform consistency is obtained.

PLACING AND FINISHING

Vertical Application

KingGrout PE10 V should be used for vertical applications. The mixed material should be poured into the prepared holes. The bar/bolt should then be pressed and twisted into the grout.

Horizontal Application

KingGrout PE10 H should be used for horizontal applications. Grouting can be carried out by filling the materials into plastic Cartridges and then injected using a skeleton gun. Once the grout is injected, the bar/bolt should be pressed and twisted into the grout.

Care should be taken to ensure that the bottom and the side are thoroughly scraped and transferred. The filler shall be gradually added to the plastic container containing the resin while mixing.

KingGrout® PE10

High strength polyester grout for anchoring and fixing.

TABLE I	FY (N/mm ²)	FC (N/mm ²)	ΦB (mm)	ΦH (mm)	Calculated Pullout Force F(KN) in tension with 40% safety margin at a certain hole depth (HD)	Ultimate Pullout Force in tension	D) To calculate volume of Keyfix P required in ML: Volume (ML) = π . (ΦH ² - ΦB ²) . HD 4000												
							TABLE III	Volume of KEYFIX REQUIRED (ML)	Hole Depth (mm)	Bar Dia mm	100	140	160	200	250	300	350	400	
For Steel Bar	For Concrete	Bar Diameter	Hole Diameter	100	120	180	200	250	300	350	400	100	140	160	200	250	300	350	400
420	2.5	8	12	16	19	25	37	52	72	99	134	180	227	287	361	451	558	683	827
420	2.5	10	14	18	22	29	42	59	81	111	150	199	260	333	419	518	631	758	900
420	2.5	12	16	21	25	33	47	65	90	123	166	219	284	361	451	555	674	808	957
420	2.5	14	18	24	28	38	53	73	100	135	181	239	309	392	489	599	724	864	1019
420	2.5	16	20	26	31	42	58	80	108	146	195	256	329	415	514	626	751	890	1044
420	2.5	18	22	29	35	46	63	86	116	157	209	274	351	441	544	660	789	932	1090
420	2.5	20	24	31	38	50	68	92	124	167	222	289	369	462	568	686	817	962	1122
420	2.5	22	26	34	41	54	73	98	132	177	234	303	385	480	588	709	844	994	1159
420	2.5	25	30	39	47	61	81	107	143	191	251	323	407	504	614	737	874	1026	1193
420	2.5	32	36	47	56	72	94	122	161	212	276	353	444	549	668	799	944	1104	1279

C) Table II shown below shows the Ultimate Pullout Force that each steel reinforcement bar grade 60 can take:

TABLE II	Dar Diameter ΦB mm	Bar Area mm	FY N/mm ²	Ultimate Pullout Force (F) KN
8	50.24	420	21	
10	78.5	420	33	
12	113.04	420	47	
14	153.86	420	65	
16	200.96	420	84	
18	254.34	420	107	
20	314	420	132	
22	379.94	420	160	
25	490.625	420	206	
32	803.84	420	338	

As per BS8110, minimum Hole Depth HD (or length of embedment) is shown below, allowing for 40% factor of safety

$$HD = 0.6 \cdot FY \cdot \pi \cdot \Phi B^2$$

$$FC \cdot \pi \cdot \Phi H \cdot 4$$

$$HD = 0.6 \cdot FY \cdot \Phi B^2$$

$$4 \cdot FC \cdot \Phi H$$

Noting that:

FY: Yield strength of the steel (N/mm²)

FC: Concrete bond stress (N/mm²)

ΦB: Bar Diameter (mm)

ΦH: Hole Diameter (mm)

HD: Minimum Hole Depth (length of Embedment) (mm)

π: 3.14

B) Calculation of the Pullout Force (F) in tension using the minimum hole depth (HD) shown in A is as follows:

$$HD = 0.6 \cdot FY \cdot \Phi B^2$$

$$4 \cdot FC \cdot \Phi H$$

$$FC \cdot \pi \cdot \Phi H \cdot HD = 0.6 \cdot FY \cdot \pi \cdot \Phi B^2$$

KingGrout® PE10

High strength polyester grout for anchoring and fixing.

4

The Pullout Force (F) is equal to $FY \cdot \text{Steel Bar Area}$. The Steel Bar Area is equal to:

$$\pi \Phi B^2$$

4

then:

$$FC \pi \Phi H HD = 0.6 F$$

$$F (N) = \pi \cdot FC \cdot \Phi H \cdot HD$$

0.6

$$F (KN) = (5.23 \cdot FC \cdot \Phi H \cdot HD^4) \div 1000$$

Table I is a summary of the forces (F) that each steel reinforcement bar can take for a certain hole depth (HD).

Calculations are based on steel grade 60 and 25 N/ mm² concrete compressive strength with FC at 2.5 N/ mm².

ESTIMATING

The required quantity of grout needed is dependent on hole diameter, bar diameter and hole depth. This can be estimated by using the following formula:

$$\text{Volume of grout (ml)} = 3.14 \cdot (Dh^2 - Db^2) \cdot H$$

4

Where:

Dh is hole diameter in mm.

Db is bar diameter in mm.

H is hole depth in mm

CLEANING

All tools should be cleaned immediately after finishing by KINGKRETE Solvent. Hardened materials can be cleaned mechanically.

PACKAGING

KingGrout PE10 is available in 1.2 litre packs.

STORAGE

Shelf life is 1 year when stored under cover, out of direct sunlight and protected from extremes of temperature.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult KingKrete's Technical Services Department.

HEALTH AND SAFETY

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs. Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Reseal containers after use. Use in well ventilated areas and avoid inhalation.

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local KingKrete representative. KingKrete Inc. reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY AND CARE

All products originating from KingKrete's Middle East facility are manufactured under a management system independently certified to conform to the requirements of the quality standards ISO 9001, ISO 14001 and ISO 45001.

* Properties listed are based on laboratory-controlled tests.

® = Registered trademark of the KingKrete-Group in many countries.

Ref: KK-04017-MEA-R01 | Issue: 01.2026

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this KingKrete Inc. publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by KingKrete Inc. either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not KingKrete Inc. are responsible for carrying out procedures appropriate to a specific application.