

KingFloor® EPL

Low duty epoxy floor coating for vehicle decking system.

DESCRIPTION

KingFloor EPL is a hard wearing, epoxy base coating system primarily designed for use in car parks. It has excellent resistance to petrol, battery acid, diesel, brake fluid, de-icing salts, etc. KingFloor EPL System is formulated for easy application by roller or brush.

KingFloor EPL is multi-layer system consists of the following:

KingFloor EP100, a primer with excellent adhesion to concrete substrates.

KingFloor EP50, a high build epoxy coating.

APPLICATIONS

KingFloor EPL System is designed for use in applications, such as:

- ☐ Car park decks.
- ☐ Car park ramps and turning circles.
- ☐ Traffic aisles and parking bays.
- ☐ Road marking.

ADVANTAGES

- ☐ Seamless.
- ☐ Excellent chemical resistance.
- ☐ Excellent resistant to petrol, battery acid, diesel and brake fluid.
- ☐ Resistant to de-icing.

SYSTEM SPECIFICATION

The combination of products specified depends on the area within the car part to which the KingFloor EPL System is being applied.

CAR PARK DECKS

Ramps and turning circles

- ☐ KingFloor EP100.
- ☐ First coat of KingFloor EP50.
- ☐ Two coats of KingFloor EP50.

Traffic aisles and parking bays

- ☐ KingFloor EP100.
- ☐ One coat of KingFloor EP50.
- ☐ One coat of KingFloor EP50.

METHOD OF USE

KINGFLOOR EP100

Surface Preparation and Priming

To obtain a proper bond the substrate must be structurally sound clean, dry (less than 75% RH measured using a hygrometer, unless it is a suspended deck free to dry from below) and free from dust, laitance, oils, paints or other forms of contamination. Grit blasting, grinding or scarification can be used to remove laitance and surface contamination.

Areas known to have been subject to heavy contamination should be thoroughly inspected before applying KingFloor EP100. This is especially important where deposits of oil or grease have collected. Any irregularities within the substrate should be made good before the application of the Prime coat. Small defects may be made good using suitable repair materials such as KingKrep range or epoxy putty "KingRep EP10".

MIXING

KingFloor EP100 comprises three components; a resin, hardener and colour pack which are supplied pre-weighed in the correct proportions. Under no circumstances should part mixing be carried out.

Taking care to ensure that the bottom and sides are thoroughly drained, pour the contents of the hardener portion into the resin container. Using a power whisk attached to a slow speed electric drill, mix for approximately 2 minutes, scrape down and re-mix for a further 1 minute, avoiding the entraining of excessive air, until a uniform consistency is obtained add the colour pack and further mix for 2 minutes. Allow to stand for 1 minute.

Note: Never mix KingFloor Primer 10 by hand as this could lead to areas of uncured material.

APPLICATION

Once mixing is complete, spread the KingFloor EP100 onto the floor using a medium pile roller, ensuring it is worked well into the surface.

Overcoating

KingFloor EP100 may be over coated as soon as it becomes tack free. If over coating of the KingFloor EP100 exceeds 30 hours, light scarification of the surface should be undertaken before further applications of KingFloor EP50.

KINGFLOOR EP50

KingFloor® EPL

Low duty epoxy floor coating for vehicle decking system.

SURFACE PREPARATION

All surfaces should be primed with KingFloor EP100 before applying KingFloor EP50.

MIXING

KingFloor EP50 comprises three components, a resin, hardener and colour pack which are supplied pre-weighed in the correct proportions. Under no circumstances should part mixing be carried out.

Pre-mix the resin component with a power whisk attached to a slow speed electric drill for 1 minute before mixing both components.

Taking care to ensure that the bottom and sides are thoroughly scraped, transfer the contents of the resin in to the hardener. Using a power whisk attached to a slow speed electric drill, mix for approximately 3 minutes, ensuring the mixing head is pushed around the sides and bottom of the mixing container. Transfer the contents into another container, scraping down and re-mixing for a further 2 minutes avoiding the entraining of excessive air until a uniform consistency is obtained. Add the colour pack and further mix for 2 minutes.

APPLICATION

Immediately after mixing is complete, spread the KingFloor EP50 onto the primed floor using a short or medium pile roller.

CLEANING

Tools should be cleaned with KingFloor Solvent immediately after use.

PACKAGING

KingFloor EP100 is available in 5 and 20 kg packs. KingFloor EP50 is available in 5 and 20 kg packs.

COVERAGE

The coverage obtained will vary depending on the porosity and texture of the surface to which the System materials are applied and, if applicable, the type and size of aggregate used. As a guide, the minimum coverage (per coat) should be as follows:

- KingFloor EP100: 0.2 kg/m².
- KingFloor EP50: 0.30 kg/m².

STORAGE

Shelf life is 1 year when stored under cover, out of direct sunlight and protected from extremes of temperature. Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult KingKrete's Technical Services Department.

HEALTH AND SAFETY

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs. Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Reseal containers after use. Use in well ventilated areas and avoid inhalation.

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local KingKrete representative. KingKrete Inc. reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY AND CARE

All products originating from KingKrete's Middle East facility are manufactured under a management system independently certified to conform to the requirements of the quality standards ISO 9001, ISO 14001 and ISO 45001.

* Properties listed are based on laboratory-controlled tests.

® = Registered trademark of the KingKrete-Group in many countries.



KingFloor® EPL

Low duty epoxy floor coating for vehicle decking system.

Ref: KK-07038-MEA-R01 | Issue: 01.2026

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this KingKrete Inc. publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by KingKrete Inc. either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not KingKrete Inc. are responsible for carrying out procedures appropriate to a specific application.

KingKrete Middle East
Qatar – Syria
www.kingkrete.com

Disclaimer: the IAS mark relates to certified management system and not to the product mentioned on this datasheet

