

KingProof® B500

Water based elastomeric rubberized bitumen waterproof coating.

DESCRIPTION

KingProof B500 is a water based bitumen waterproof coating modified with acrylic polymers, formulated from selected raw materials to form a high build elastomeric waterproof and protective coating for concrete and masonry.

APPLICATIONS

KingProof B500 provides a waterproof coating for:

- ☒ Retaining walls.
- ☒ Foundations and basements.
- ☒ Wet areas (Under Tiles).
- ☒ Repairs of existing bitumen surfaces and membranes.
- ☒ Shaded or tiled roofs.

ADVANTAGES

- ☒ One component – ready to use.
- ☒ Elastomeric will bridge minor cracks which may occur in concrete substrates.
- ☒ Extremely high elongation.
- ☒ Excellent adhesion to a wide range of substrates.
- ☒ Resists attack by chloride and sulphate ions present in ground water.
- ☒ Solvent free, non-flammable.
- ☒ Asbestos free.
- ☒ Rot resistant.

STANDARDS

- ☒ KingProof B500 matches the physical properties of ASTM D1227-13, Type II, Class 1.
- ☒ KingProof B500 complies with ASTM C309 as a curing compound when applied with two coats at a rate of 4 m²/litre per coat.

METHOD OF USE

SURFACE PREPARATION

Surface preparation is very important to get the highest performance of KingProof B500. Any surface to be coated must be clean, sound and free of oil or grease.

Any oil or grease contamination should be removed with a chemical degreaser. All holes should be filled with a suitable cementitious mortar before application of KingProof B500.

TECHNICAL PROPERTIES

Form:	Liquid
Specific gravity:	1.07 ± 0.03
Solid content:	55 ± 2%
Over coating time	4 - 6 hr
Elongation ASTM D412	≥ 850% @ 7 days
Tensile strength: ASTM D412	≥ 0.20 MPa @ 7 days
Water permeability: DIN1048 (5 bars)	0%

PRIMING

There is generally no need for primer coat. Dusty surfaces should be primed with a coat of KingProof B500, diluted with an equal quantity of cool, clean water and allowed to dry.

APPLICATION

It is recommended that two coats of KingProof B500 be applied. The second coat should be applied at a right angle to the first coat. Allow 4 - 6 hours between coats. Stir well before use. KingProof B500 may be applied by brush, broom or squeegee.

COVERAGE

- ☒ 3 - 5 m²/litre per coat, as protective coating.
- ☒ 1 - 1.5 m²/litre per coat, as water proof coating giving a dry film thickness of 500 microns per coat. Two coats recommended.

CLEANING

Tools and equipment can be cleaned with water when still wet.

Dried KingProof B500 may be removed with DCP Solvent.

PACKAGING

KingProof B500 is available in 18 and 200 litre drums.

STORAGE

Shelf life is 1 year when stored under cover, out of direct sunlight and protected from extremes of temperature.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult KingKrete's Technical Services Department.



KingProof® B500

Water based elastomeric rubberized bitumen waterproof coating.

HEALTH AND SAFETY

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs. Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Reseal containers after use. Use in well ventilated areas and avoid inhalation.

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local KingKrete representative. KingKrete Inc. reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY AND CARE

All products originating from KingKrete's Middle East facility are manufactured under a management system independently certified to conform to the requirements of the quality standards ISO 9001, ISO 14001 and ISO 45001.

* Properties listed are based on laboratory-controlled tests.
® = Registered trademark of the KingKrete-Group in many countries.

Ref: KK-08014-MEA-R01 | Issue: 01.2026

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this KingKrete Inc. publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by KingKrete Inc. either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not KingKrete Inc. are responsible for carrying out procedures appropriate to a specific application.

