

KingProof® PUB200

Two component polyurethane-bitumen liquid membrane for waterproofing.

DESCRIPTION

KingProof PUB200 is a two-part polyurethane waterproofing coat extended with chemically polymerized virgin bitumen.

KingProof PUB200 has excellent adhesion to many substrates producing a highly elastic membrane with excellent chemical resistance properties.

APPLICATIONS

Waterproofing and protection of:

- ☒ Basement and foundation.
- ☒ Irrigation channels.
- ☒ Gypsum and cement boards.
- ☒ Polyurethane insulation foams.
- ☒ EPDM membrane.
- ☒ Roofs.
- ☒ Asphalt membrane.
- ☒ Under tiles of bathrooms and balconies.
- ☒ Light roofing made of metal.
- ☒ Bridge platforms.
- ☒ Planters, roof-top gardens and flower pots.
- ☒ Lining of manholes.
- ☒ Tanks containing waste water.

ADVANTAGES

- ☒ Excellent adhesion on many substrates.
- ☒ Fast curing.
- ☒ Good water vapour barrier.
- ☒ Good chemical resistance.
- ☒ Wide temperature resistance.
- ☒ Excellent mechanical properties.

STANDARDS

KingProof PUB200 complies with ASTM C836-95.

METHOD OF USE

SURFACE PREPARATION

The surface should be clean, dry, sound and free from oil, grease and wax contamination.

Cement laitance, loose particles, mould release agent or curing membranes must be removed.

TECHNICAL PROPERTIES

Specific gravity	0.95 ± 0.05
Tack free time:	1 - 2 hr @ 25°C & 55% RH
Recoat time:	6 - 24 hr
Pot life	30 - 45 min @ 20oC
Service temperature	-40 to 80oC
Viscosity of mixture: ASTM D2196-86	3000 cp @ 25oC
Hardness shore A: ASTM D2240, DIN 53505, ISO R868	35
Tensile strength at break: ASTM D412, DIN 52455	2 MPa @ 23°C
Elongation: ASTM D412, DIN 52455	> 1000%
Maximum shock temperature:	150oC
QUV accelerated weathering test: ASTM G53	Passed (1000 hr)
Hydrolysis resistance (8% KOH, 10 days @ 50°C):	No significant elastomeric property change
Chemical resistance: (5% NaClO, 10 days)	No significant elastomeric property change
Water absorption: (10 days)	< 0.9%
Thermal resistance: (200 days @ 80oC) EOTA TR011	Passed

PRIMING

It is recommended to use KingProof MPU Primer with consumption of 150 to 200 gr/m². KingProof MPU Primer should be left for 12 - 24 hours to fully cure depending on ambient conditions.

MIXING

Mix equal volumes of the two components manually or with a low speed (300 rpm) mixer. The pot life is between 30 and 45 minutes at 20oC.

APPLICATION

KingProof PUB200 can be applied using a brush, roller or airless spraying machine. For the application using a spraying machine add 5 to 10% of KINGKRETE Solvent PU to thin the mixture. For any cracks larger than 1 mm, KingProof PUB200 can be used to close them prior to the application of the main coat.

KingProof® PUB200

Two component polyurethane-bitumen liquid membrane for waterproofing.

CLEANING

All tools should be cleaned after finishing with paper towels and then wipe by using KINGKRETE Solvent PU. Do not try to clean rollers.

PACKAGING

KingProof PUB200 is available in 2 x 5 litre, 2 x 20 litre or 2 x 200 litre packages.

KingProof MPU Primer is available in 5 or 10 litre package.

CONSUMPTION

KingProof PUB200 should be applied at a minimum consumption of 1.0 - 1.5 ltr/m².

STORAGE

Shelf life is 1 year when stored under cover, out of direct sunlight and protected from extremes of temperature.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult KingKrete's Technical Services Department.

HEALTH AND SAFETY

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs. Treat splashes to eyes

and skin immediately. If accidentally ingested, seek medical attention. Reseal containers after use. Use in well ventilated areas and avoid inhalation.

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local KingKrete representative. KingKrete Inc. reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY AND CARE

All products originating from KingKrete's Middle East facility are manufactured under a management system independently certified to conform to the requirements of the quality standards ISO 9001, ISO 14001 and ISO 45001.

* Properties listed are based on laboratory-controlled tests.

® = Registered trademark of the KingKrete-Group in many countries.

Ref: KK-08038-MEA-R01 | Issue: 01.2026

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this KingKrete Inc. publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by KingKrete Inc. either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not KingKrete Inc. are responsible for carrying out procedures appropriate to a specific application.